

high performance fluoropolymer and fluoroplastic tubing and pipe

ALTAFLUOR 500®

PVDF (Polyvinylidene Fluoride) is an abrasion resistant fluoropolymer suitable for use in applications requiring chemical resistance with low permeability. Altafluor 500 PVDF is the most abrasion and temperature resistant of the PVDF products offered. Altafluor 500 provides excellent abrasion resistance and mechanical strength in use with many chemicals and solvents. With its extremely low extractable levels, Altafluor 500 is excellent for use in ultra pure water systems. Altafluor 500 is suitable for use with conventional fittings but is not recommended for use with flare fittings.

ALTAFLUOR 500® Features

- 100% virgin grade KYNAR® PVDF
- Excellent abrasion resistance
- Low permeability
- Good chemical resistance
- UV resistant
- FDA Compliant

Applications

- Chemical process
- Semiconductor
- Water process systems
- Aquarium

Specifications

General: Resins meet or exceed requirements listed in ASTM D 3222

Temperature: -20° F to 250° F

Flammability: UL 94-V0 rated KYNAR® PVDF resists combustion and does not promote flame spread

FDA: KYNAR® PVDF is approved for use in food contact applications in compliance with FDA regulation 21 CFR 177.1500

ALTAFLUOR 500® – PVDF Tubing

PART NUMBER	ID	OD	+/-	WALL	+/-
-------------	----	----	-----	------	-----

ALTAFLUOR 500 is produced from a KYNAR® homopolymer PVDF resin and is available as a custom order. Minimum order requirements apply. Please consult factory for sizes and availability.

For Flexible PVDF, please see ALTAFLUOR 550 series.

ALTAFLUOR 500® Series PVDF – Physical Properties

PHYSICAL PROPERTY	ASTM TEST METHOD	UNITS	VALUES
Upper Service Temp			250° F
Specific Gravity	D 792		1.77-1.79
Tensile Strength	D 1708	PSI	5000-7000
Elongation	D 638	%	50-200
Flex Modulus	D 790	PSI	240,000-300,000
Hardness	D 2240	Shore D	76-80

The above information is based on tests performed at 73° F and can vary in individual applications based on parameters such as temperature, chemical concentration, pressure, etc. Please consult factory for details.



25 weldon road
lake hopatcong, nj 07849

973-663-3303

sales@altaflo.com

www.altaflo.com

Transport Critical Fluid With Confidence™

ALTAFLUOR® is a registered trademark of Altaflo LLC

KYNAR® and KYNAR FLEX® are registered trademarks of Arkema Inc.

Teflon® is a registered trademark of E.I. Dupont

Neoflon® is a registered trademark of Daikin