

# high performance fluoropolymer and fluoroplastic tubing and pipe

## ALTAFLUOR 600®

MFA (perfluoro methyl alkoxy) is a co-polymer of tetrafluoroethylene and perfluoromethyl vinyl ether. MFA is similar in characteristics and performance to PFA.

Like PFA resins, ALTAFLUOR 600 resins provide excellent stress crack and chemical resistance. It has purity levels equal or better than most standard PFA resins. Additionally, the ultra-smooth surface finish of ALTAFLUOR 600 tubing products make them ideal for applications requiring quick and easy clean out. MFA has superior clarity than PFA in UV and visible spectrums. For chemical applications not exceeding 480 °F, ALTAFLUOR 600 tubing may prove to be a cost effective option. ALTAFLUOR 600 tubing may be used with flare or conventional fittings.

### ALTAFLUOR 600® Features

- 100% virgin grade high performance resin
- Chemically inert to nearly all industrial chemicals and solvents
- Better clarity than PFA in UV and visible spectrums
- Higher service temperature than FEP
- Lower permeability than FEP
- Better impact resistance than PFA
- Smoother surface finish than PFA
- Lower extractable levels than standard FEP and PFA
- Moisture absorption nearly zero
- Non-flammable
- Excellent electrical insulation
- Available coiled

### Applications

- Chemical process
- Paint spray
- Electrical insulation
- Heat exchangers
- Semiconductor
- Automotive

### Specifications

**General:** Meets or exceeds the requirements of ASTM 6314

**Temperature:** -100 °F to 482 °F

**Flammability:** UL 94 VO rated. MFA resists combustion and does not promote flame spread

### ALTAFLUOR 600® – MFA Tubing

PART NUMBER	ID	OD	+/-	WALL	+/-
-------------	----	----	-----	------	-----

Please consult factory for sizes and availability.

### ALTAFLUOR 600® Series MFA – Physical Properties

PHYSICAL PROPERTY	ASTM TEST METHOD	UNITS	VALUES
Upper Service Temp			450° F
Specific Gravity	D 792		2.15
Tensile Strength	D 1708	PSI	4500
Elongation	D 638	%	330
Flex Modulus	D 790	PSI	65,000
MIT Flex Life	D 2176		80,000
Hardness	D 2240	Shore D	59

The above information is based on tests performed at 73° F and can vary in individual applications based on parameters such as temperature, chemical concentration, pressure, etc. Please consult factory for details.



25 weldon road  
lake hopatcong, nj 07849

973-663-3303

sales@altaflo.com

[www.altaflo.com](http://www.altaflo.com)

*Transport Critical Fluid With Confidence™*

ALTAFLUOR® is a registered trademark of Altaflo LLC

Teflon® is a registered trademark of E.I. DuPont

Neoflon® is a registered trademark of Daikin