

PTFE (polytetrafluoroethylene) was the original Teflon material first developed by the E.I. DuPont Co. PTFE is the most flexible of all fluoropolymers offered. ALTAFLUOR® 100 PTFE has the broadest temperature range of any fluoropolymer and can resist highly corrosive liquids and gases even at elevated temperatures. The smooth surface finish and lowest coefficient of friction and lubricity make it ideal for bushing or bearing applications. Lengths may be limited due to batch size - please call to confirm available lengths at time of order. ALTAFLUOR® 100 is compatible with most standard fittings (not suitable for use with flare-type fittings).

### ALTAFLUOR® 100 FEATURES

- 100% virgin grade PTFE resins
- Most flexible fluoropolymer
- Chemically inert and resistant to nearly all industrial chemicals and solvents
- Low permeability
- Smooth non-stick surface finish
- Lowest coefficient of friction
- Excellent electrical properties
- Non-Flammable
- Non-Toxic
- FDA Compliant
- Suitable for use with conventional fittings

### APPLICATIONS

- Laboratory
- Chemical Process
- Analytical and process equipment
- Cryogenic applications
- Electrical applications
- High Temperature applications
- Automotive

### SPECIFICATIONS

**General:** Meets or exceeds the requirements listed in ASTM D 3295 (except for dimensional on specific items)

**Temperature:** -410° F to 500° F continuous / 550° F short-term

**Flammability:** PTFE tubing resists combustion and does not promote flame spread. PTFE resin used for production of ALTAFLUOR® 100 series is UL 94 V0 rated

**FDA:** PTFE is approved for use in food contact applications in compliance with FDA regulation: 21 CFR 177.1550

### ALTAFLUOR® 100 PTFE - TUBING

PART NUMBER	ID	OD	+/-	WALL	+/-
100-0125-030-XX	1/16	1/8	.005	0.030	.005
100-0188-030-XX	1/8	3/16	.005	0.030	.005
100-0250-030-XX	3/16	1/4	.005	0.030	.005
100-0313-030-XX	1/4	5/16	.005	0.030	.005
100-0375-030-XX	5/16	3/8	.005	0.030	.005
100-0500-030-XX	7/16	1/2	.005	0.030	.005
100-0250-040-XX	.170	1/4	.005	0.040	.005
100-0250-047-XX	.156	1/4	.005	0.047	.005
100-0250-062-XX	1/8	1/4	.005	0.062	.005
100-0313-062-XX	3/16	5/16	.005	0.062	.005
100-0375-062-XX	1/4	3/8	.005	0.062	.005
100-0500-062-XX	3/8	1/2	.005	0.062	.005
METRIC SIZES	ID	OD	+/-	WALL	+/-
100-0157-040-XX	2mm	4mm		1mm	
	.079	.157	.005	0.040	.005
100-0236-040-XX	4mm	6mm		1mm	
	.157	.236	.005	0.040	.005
100-0315-040-XX	6mm	8mm		1mm	
	.236	.315	.005	0.040	.005
100-0394-040-XX	8mm	10mm		1mm	
	.315	.394	.005	0.040	.005
100-0472-040-XX	10mm	12mm		1mm	
	.394	.472	.005	0.040	.005
100-0354-059-XX	.6mm	9mm		1.5mm	
	.236	.354	.005	.059	.005
100-0472-059-XX	.9mm	12mm		1.5mm	
	.354	.472	.005	.059	.005

Stocked in natural color - please consult factory for details on available colors.



P: 973-300-3344

F: 973-300-3345

E: sales@altaflo.com

A: 23 Wilson Drive, Sparta, NJ 07871

ALTAFLUOR® is a registered trademark of Altaflo LLC

TEFLON™ is a brand of Chemours

NEOFLO® is a registered trademark of Daikin

KYNAR® and KYNAR FLEX® are registered trademarks of Arkema Inc.

Due to the nature of applications involving the use of fluoropolymers, we suggest that all customers test product within the conditions specific to their application prior to use.

#### ALTAFLUOR® 100 PTFE - BEND RADIUS AND WORKING PRESSURE CHART

PART NUMBER	OD	WALL	ID	BEND RADIUS	WORKING PRESSURE @ 73°F
100-0062-015-XX	0.062	0.015	0.032	1/2"	419
100-0094-030-XX	0.094	0.03	0.032	1/2"	549
100-0125-030-XX	0.125	0.030	0.062	1/2"	443
100-0188-030-XX	0.188	0.030	0.125	3/4"	254
100-0250-030-XX	0.250	0.030	0.188	1"	172
100-0250-040-XX	0.250	0.040	0.170	1"	310
100-0250-047-XX	0.250	0.047	0.156	3/4"	360
100-0250-062-XX	0.250	0.062	0.125	1/2"	398
100-0313-030-XX	0.313	0.030	0.250	1-3/4"	120
100-0313-062-XX	0.313	0.062	0.188	1"	356
100-0375-030-XX	0.375	0.030	0.313	1-3/4"	100
100-0375-062-XX	0.375	0.062	0.250	3/4"	248
100-0500-030-XX	0.500	0.030	0.438	6"	71
100-0500-062-XX	0.500	0.062	0.375	2-1/2"	150
METRIC SIZES	ID	WALL	ID	BEND RADIUS	WORKING PRESSURE @ 73°F
100-0157-040-XX	0.157	0.04	0.079	3/4"	455
	4mm	1mm	2mm		
100-0236-040-XX	0.236	0.040	0.157	1"	208
	6mm	1mm	4mm		
100-0315-040-XX	0.315	0.040	0.236	1-1/2"	156
	8mm	1mm	6mm		
100-0394-040-XX	0.394	0.040	0.315	2"	125
	10mm	1mm	8mm		
100-0472-040-XX	0.472	0.040	0.394	4"	104

The above information is based on tests performed at 73° F and can vary in individual applications based on parameters such as temperature, chemical concentration, pressure, etc. Please consult factory for details. For an estimate on burst pressure at ambient temperature we consider a 3:1 ratio when exposure temperature is 73° F. However Altaflo does not recommend exceeding the suggested Working Pressure listed.

#### ALTAFLUOR® 100 PTFE - PHYSICAL PROPERTIES

PHYSICAL PROPERTY	ASTM TEST METHOD	UNITS	VALUES
Upper Service Temp. Long Term			500° F
Upper Service Temp. Short Term			550° F
Specific Gravity	D 792		2.15
Tensile Strength	D 1708	PSI	2500-3000
Elongation	D 638	%	200-400
Flex Modulus	D 790	PSI	27,000
MIT Flex Life	D 2176		1,000,000+
Hardness	D 2240	Shore D	60



P: 973-300-3344

F: 973-300-3345

E: sales@altaflo.com

A: 23 Wilson Drive, Sparta, NJ 07871

ALTAFLUOR® is a registered trademark of Altaflo LLC

TEFLON™ is a brand of Chemours

NEOFLO® is a registered trademark of Daikin

KYNAR® and KYNAR FLEX® are registered trademarks of Arkema Inc.