

ALTAFLUOR® 2E0

ALTAFLUOR® 2E0 ENVIRO SERIES FEP (fluorinated ethylene propylene), is designed specifically for use in environmental sampling applications. This cost effective choice is the preferred product for applications requiring the purity of FEP without exposure to aggressive chemical or other harsh conditions. ALTAFLUOR® 2E0 Series FEP does not impart taste, odor or other contaminants. For more critical application requirements, we suggest the use of ALTAFLUOR® 200 FEP or ALTAFLUOR® 400 PFA Tubing.

ALTAFLUOR® 2E0 FEATURES

- Excellent UV transmission
- Low permeability
- High thermal stability
- Excellent clarity
- Moisture absorption nearly zero
- Does not impart taste, odor or contaminants
- Non-flammable

APPLICATIONS

- Ground water monitoring
- Air sampling
- Laboratory applications
- Water process
- UV water purification systems

SPECIFICATIONS

General: FEP meets the requirements listed in ASTM D2116

Temperature: -100°F to 400°F

Flammability: FEP is non-combustible and does not promote flame spread

ALTAFLUOR® 2E0 FEP ENVIRO - ENVIRO TUBING

PART NUMBER	ID	OD	+/-	WALL	+/-
2E0-0250-030-XX	3/16	1/4	.005	.030	.003
2E0-0313-030-XX	1/4	5/16	.005	.030	.003
2E0-0375-030-XX	5/16	3/8	.005	.030	.003
2E0-0500-030-XX	7/16	1/2	.005	.030	.003
2E0-0250-040-XX	.170	1/4	.005	.040	.003
2E0-0375-062-XX	1/4	3/8	.005	.062	.003
2E0-0500-062-XX	3/8	1/2	.005	.062	.003

Additional sizes up to 3" OD are available as custom extrusions - minimum order requirements may apply. Please contact Altaflo office for details. This tubing is not recommended for aggressive chemical applications - please refer to ALTAFLUOR® 200 or ALTAFLUOR® 400.

ALTAFLUOR® 2E0 FEP ENVIRO - BEND RADIUS AND WORKING PRESSURE CHART

PART NUMBER	OD	WALL	ID	BEND RADIUS	WORKING PRESSURE @ 73°F
2E0-0250-030-XX	0.188	0.250	.030	1"	195
2E0-0313-030-XX	0.250	0.313	.030	1-3/4"	156
2E0-0375-030-XX	0.313	0.375	.030	2-1/2"	130
2E0-0500-030-XX	0.438	0.500	.030	6"	97
2E0-0250-040-XX	0.170	0.250	.040	1"	260
2E0-0375-062-XX	0.250	0.375	.062	1"	269
2E0-0500-062-XX	0.375	0.500	.062	2"	200

The above information is based on tests performed at 73° F and can vary in individual applications based on parameters such as temperature, chemical concentration, pressure, etc. Please consult factory for details. For an estimate on burst pressure at ambient temperature we consider a 3:1 ratio when exposure temperature is 73° F. However Altaflo does not recommend exceeding the suggested Working Pressure listed.

ALTAFLUOR® 2E0 FEP ENVIRO - PHYSICAL PROPERTIES

PHYSICAL PROPERTY	ASTM TEST METHOD	UNITS	VALUES
Upper Service Temp. Long Term			400° F
Specific Gravity	D 792		2.12-2.17
Tensile Strength	D 1708	PSI	3500
Elongation	D 638	%	300-400
Flex Modulus	D 790	PSI	90,000
MIT Flex Life	D 2176		5000
Hardness	D 2240	Shore D	57-60



P: 973-300-3344

F: 973-300-3345

E: sales@altaflo.com

A: 23 Wilson Drive, Sparta, NJ 07871

ALTAFLUOR® is a registered trademark of Altaflo LLC

TEFLON™ is a brand of Chemours

NEOFLON® is a registered trademark of Daikin

KYNAR® and KYNAR FLEX® are registered trademarks of Arkema Inc.