

# Altaflo Material Selection Chart

	ASTM TEST	100 (PTFE)	200 (FEP)	2E0 (FEP)	350 (THV)	400 (PFA)	480 (UHP PFA)	500 (PVDF)	550 (PVDF FLEX)	600 (MFA)	700 (ETFE)
UPPER SERVICE TEMP. °F		500° F*	400° F	400° F	180° F	500° F	500° F	250° F	212° F	480° F	300° F
SPECIFIC GRAVITY	D 792	2.15	2.15	2.12-2.17	1.95	2.15	2.15	1.77-1.79	1.78	2.15	1.74
TENSILE STRENGTH PSI	D 1708	2500-3000	4000	3500	2900	4200	4500	5000-7000	3500	4500	3100-6800
ELONGATION %	D 638	200-400	400	300-400	600	400	400	50-200	200-500	330	420-450
FLEX MODULUS PSI	D 790	27,000	90,000	90,000	12,000	90,000	90,000	240,000-300,00	40,000-60,000	65,000	128,000-171,000
MIT FLEX LIFE	D 2176	1,000,000+	200,000	5000	N/A	500,000+	1,750,000	N/A	N/A	80,000	N/A
HARDNESS - SHORE D	D 2240	60	57-60	57-60	44	60	60	76-80	57-62	59	75

The above information is based on tests performed at 73° F and can vary in individual applications based on parameters such as temperature, chemical concentration, pressure, etc. Please consult factory for details.

\*ALTAFLUOR 100 ® SERIES PTFE Short Term Upper Service Temp: 550° F.

ALTAFLUOR® is a registered trademark of Altaflo LLC

TEFLON™ is a brand of Chemours

NEOFLON® is a registered trademark of Daikin

KYNAR® and KYNAR FLEX® are registered trademarks of Arkema Inc.

P: 973-300-3344

F: 973-300-3345

E: sales@altaflo.com

A: 23 Wilson Drive, Sparta, NJ 07871

